

# **TECHNICAL DATA SHEET**

## **Product Description**

B-5107, B-5117 and B-5118 are temporary protective coatings in aerosol form for use as marking colors on dry film of BMS 15-12 Type I Class 1 temporary protective coating.

- Chromate free
- Water-based
- Non-flammable
- Available in black (B-5107), red (B-5117) and white (B-5118)

## Components



#### Mix ratio (by volume):

B-5107, B-5117 and B-5118 are packaged in ready to use aerosol cans

## **Specifications**



B-5107, B-5117 and B-5118 are qualified to the following specifications:

• BMS 15-12 Type I Class 5

Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.

#### **Product Compatibility:**

B-5107, B-5117 and B-5118 are compatible with the following specifications:

BMS 15-12 Type I Class 1, 4 & 6

# **Surface Preparation and Pretreatments**



Apply to clean temporary protective coatings.

# Instructions for Use



#### **Mixing Instructions:**

Shake can vigorously by hand.





#### **Induction** Time:

Not Required



Viscosity: (23°C/73°F)

Not applicable



Pot Life:

Not Applicable

# **Application Guidelines**

### **Recommended Application Conditions:**

Temperature 18 - 30°C (65 - 86°F)

Relative Humidity 20 - 90%

## Application:

Apply in multiple passes to a maximum film thickness of 1.0 dry mil.

### Removability:

B-5107, B-5117 and B-5118 are removed by applying a wet film of up to 20 mils thick of the BMS 15-12 Type II remover or SC-1101S remover. It should be allowed to soak into the temporary protective for approximately 5 to 20 minutes and then flushed off with water under pressure accompanied by mild brushing.

For spot removal, such as in areas to be riveted, toluene or denatured ethyl alcohol will readily dissolve a one mil coating of B-5107, B-5117 and B-5118. Apply the solvent with a cloth, allow a few seconds for penetration, and then wipe the area with a clean solvent-wet cloth.

These application guidelines represent PPG's best advice for usage in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.





### Theoretical Coverage:

B-5107

1.0 square meters/liter at 25 microns dry film (11.6 square feet/gallon at 1 mil dry film)

Recommended dry film thickness maximum; 25 microns (1.0 mils)

B-5117

1.1 square meters/liter at 25 microns dry film (11.8 square feet/gallon at 1 mil dry film)

Recommended dry film thickness maximum; 25 microns (1.0 mils)

B-5118

1.0 square meters/liter at 25 microns dry film (11.6 square feet/gallon at 1 mil dry film) Recommended dry film thickness maximum; 25 microns (1.0 mils)



### **Equipment:**

B-5107, B-5117 and B-5118 are packaged in ready to use aerosol cans.

#### **Equipment Cleaning:**

Not applicable

## **Physical Properties (product)**



Color: B-5107 Black

B-5117 Red B-5118 White



Gloss: Not Applicable



Dry Times	22 - 28°C (71 - 84°F)
Tack Free	20 minutes
Full Hardness	8 hours minimum





### VOC (EPA method 24):

B-5107 526 grams/liter
B-5117 525 grams/liter
B-5118 524 grams/liter



### Flash point closed cup:

This product is non-flammable

#### **Shelf Life:**

6 months from date of manufacture.

Note: Shelf life is provided for original, unopened containers.

<u>Note:</u> The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

## **Storage Recommendations**



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 13°C to 32°C (55°F to 90°F) to ensure shelf life. This is a water-base compound and should be protected from freezing. Never allow this product to freeze. Once frozen, application and protective properties are unstable and not warranted.

Note: When procuring to a qualified material specification, follow those storage instructions.



## **Health Precautions**

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure.

For industrial use only. Keep away from children.

Additional information can be found at: www.ppgaerospace.com

For sales and ordering information call the local PPG office at the numbers listed below:

## **Asia Pacific**

**ASC – Australia** Tel 61 (3) 9335 1557 Fax 61 (3) 9335 3490

**ASC – Japan** Tel 81 561 35 5200 Fax 81 561 35 5201

**ASC – South East Asia** Tel 65 6861 1119 Fax 65 6861 6162

**ASC - Suzhou** Tel (86-512) 6661 5858 Fax (86-512) 6661 6868

**ASC - Tianjin** Tel (86-022) 2482 8625 Fax (86-022) 2482 8600

## **Americas**

1 (818) 362-6711 or 1-800-AEROMIX

## **Europe and Middle East**

**ASC – Central Europe** Tel 49 (40) 742 193 10 Fax 49 (40) 742 139 69

**ASC – Middle East & India** Tel (971) 4 883 9666 Fax (971) 4 883 9665

**ASC – North Europe** Tel 44 (0) 1388 770222 Fax 44 (0) 1388 770288

**ASC – South Europe** Tel 33 (0) 235 53 43 71 Fax 33 (0) 235 53 54 44

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PRC-DeSoto International, Inc. 12780 San Fernando Road Sylmar, CA 91342

www.ppgaerospace.com

Issue Date: 11/17 Lit: 4414