

SC-1090-1 White Peelable Preservation Topcoat

TECHNICAL DATA SHEET

Product Description

SC-1090-1 is preservation topcoat designed to be used in conjunction with SC-1074A-2, SC-1074B-1 or SC-1074B-2 peelable preservation basecoats. Designed for protection of plastic, metal, porcelain and painted surfaces during in-plant fabrication, operation, shipping and storage. SC-1090-1 will provide the following to the peelable preservation basecoat: waterproof properties, both light and heat reflection, and increased weatherability.

SC-1090-1 can be applied over the preservation basecoat before it is fully dry. Therefore, it permits a very short application cycle. SC-1090-1 has the ability to dry rapidly to a rain resistant coating while at the same time allowing the preservation basecoats, SC-1074A-2, SC-1074B-1 or SC-1074B-2, to continue their curing process.

For nuclear applications, use with SC-1074B-1 or SC-1074A-2 preservation basecoats which are also rated for nuclear applications due to the low heavy metal content.

Pinholes or breaks can be patched using SC-247-2 brushable touch-up preservation topcoat.

- Water-based
- Compatible with most spray equipment
- Resistant to dirt, oil, grease and paint overspray
- Peelable with preservation basecoat
- 12 month service life when used with preservation basecoat

Components



Mix ratio (by volume):

- SC-1090-1

Single component, ready to use coating

Surface Preparation and Pretreatments



Apply to oil and dirt free surfaces.

SC-1090-1 White Peelable Preservation Topcoat

Instructions for Use

**Mixing Instructions:**


SC-1090-1 is a single component coating, no mixing required.

**Induction Time:**

Not Required

**Viscosity:** (23°C/73°F)

2,000 - 6,000 cps

**Pot Life:**

Not Applicable

Application Guidelines

Recommended Application Conditions:

Temperature	15 – 30°C (59 – 86°F)
Relative Humidity	20 – 90%

Application:

SC-1090-1 should be applied in two separate coats using air or airless equipment. The equipment recommended is Graco President or Bulldog Model pump with 205-591 Gun and standard tip with orifice of between .011 and .021 and angle between 40° and 60°. (Tip #163-617 recommended).

The first coat should be a dry coat applied with a wide fan and the gun held about 18" from the surface. This discontinuous dry coat should barely cover the preservation base coat (SC-1074B-1, SC-1074B-2 or SC1074-A2) and will minimize bubbles in the film. The second coat should be a normal spray application to build to the required 3 mils of dry film.

Special Instructions:

The preservation basecoat (SC-1074B-1, SC-1074B-2 or SC1074-A2) and SC-1090-1 preservation topcoat will reach full dryness together. Under conditions of 50% relative humidity and 21°C (70°F), about two hours drying time provides a rain resistant

SC-1090-1 White Peelable Preservation Topcoat

coating. In direct sunlight or with high air circulation and warm temperatures, the drying time is even less. Under conditions of high relative humidity, the time required for the topcoat to dry is, of course, longer. Items may be dried outdoors as long as there is no direct rain on the preserved item and temperatures are above 10°C (50°F).

These application guidelines represent PPG's best advice for usage in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.



Theoretical Coverage:

56 square meters/liter at 25 microns dry film (600 square feet/gallon at 1 mil dry film)
Recommended dry film thickness; 75 microns (3 mils)



Equipment:

SC-1090-1 is compatible with most forms of spray equipment, ~~see~~ See application section for more details.

Equipment Cleaning:

Flush spray equipment ONLY with water.

Physical Properties (product)



Color: White



Gloss: Not Applicable

Percent Solids: 48 ± 1%



Dry Times at 21 - 27°C (70 - 80°F) 50%RH

Dry through	2 hours
-------------	---------



VOC (EPA method 24):

SC-1090-1

<264 grams/liter



SC-1090-1 White Peelable Preservation Topcoat

Physical Constants:

Weight/gallon 9.3 ± 0.2 pounds/gallon



Flash point closed cup:

SC-1090-1 <42°C (107°F)


Shelf Life:

12 months from date of manufacture.

Note: Shelf life is provided for original, unopened containers.

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 13°C to 32°C (55°F to 90°F) to ensure shelf life. Never allow this product to freeze. Once frozen, application and protective properties are unstable and not warranted.

Note: When procuring to a qualified material specification, follow those storage instructions.



SC-1090-1 White Peelable Preservation Topcoat

Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

Additional information can be found at: www.ppgaerospace.com

For sales and ordering information call the local PPG office at the numbers listed below:

Asia Pacific

ASC – Australia

Tel 61 (3) 9335 1557

Fax 61 (3) 9335 3490

ASC – Japan

Tel 81 561 35 5200

Fax 81 561 35 5201

ASC – South East Asia

Tel 65 6861 1119

Fax 65 6861 6162

ASC – Suzhou

Tel (86-512) 6661 5858

Fax (86-512) 6661 6868

ASC – Tianjin

Tel (86-022) 2482 8625

Fax (86-022) 2482 8600

Americas

1 (818) 362-6711 or 1-800-AEROMIX

Europe and Middle East

ASC – Central Europe

Tel 49 (40) 742 193 10

Fax 49 (40) 742 139 69

ASC – Middle East & India

Tel (971) 4 883 9666

Fax (971) 4 883 9665

ASC – North Europe

Tel 44 (0) 1388 770222

Fax 44 (0) 1388 770288

ASC – South Europe

Tel 33 (0) 235 53 43 71

Fax 33 (0) 235 53 54 44

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PRC-DeSoto International, Inc.
12780 San Fernando Road
Sylmar, CA 91342

www.ppgaerospace.com

Issue Date: 2/16
Lit: 4484