


## PAC33 Polyurethane Primer

### Product Description

PAC33 is a two component, corrosion inhibitive, polyurethane primer modified with epoxy resin. PAC33 is designed for use with aerospace paint systems.

- Excellent corrosion resistance
- Designed for ambient curing
- High chemical resistance and flexibility
- Designed for use over P99 wash primer
- Compatible over pre-treated alloy for interior and exterior parts

### Components



#### Mix Ratio (by volume)

- |                         |           |
|-------------------------|-----------|
| • 4355/3600 (Base)      | 5 parts   |
| • 0701/9000 (Activator) | 1 part    |
| • 0433/9000 (Thinner)   | 4-5 parts |

### Specifications



PAC33 is qualified to the following OEM specifications:

- |                  |                   |
|------------------|-------------------|
| • AIMS 04-04-012 | • DGQT 1.7.0.0144 |
| • AIMS 04-04-077 | • HMDC0054        |
| • AIMS 04-04-078 | • MDL 5039        |
| • ASNA 4248      | • RPS 611         |
| • BLGG 140101    |                   |

#### Product Compatibility

PAC33 is compatible with the following:

- Sulfo-chromic or anodised pre-treated aluminium
- P99 etch primer to AIMS 04-04-012
- Polyurethane topcoat to AIMS 04-04-003 & AIMS 04-04-012

*Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.*

# PAC33 Polyurethane Primer

## Surface Preparation and Pretreatment



Ensure that the correct surface pre-treatment has been carried out, and that drying and overcoat times are observed. Ensure the surface is clean, dry and intact using high performance solvent cleaner - DeSoto® CN20 or Desoclean™ 45 solvent cleaner are recommended.

## Instructions for Use



Ensure all mixing and measuring containers are clean and free from contamination. Hand stir or mechanically agitate base material until all components are uniformly dispersed. Add activator to base, mix thoroughly and thin to recommended viscosity using approx. 4-5 volumes of thinner.

*Note: All products and components should be placed in ambient conditions of 15-35°C (59-95°F) for at least 24 hours prior to mixing and application.*



### **Induction Time:**


Not required



### **Viscosity:** (21 - 25°C / 70 - 77°F)

- |            |                 |
|------------|-----------------|
| • AFNOR2.5 | 45 - 55 seconds |
| • AFNOR4   | 14 - 16 seconds |
| • BSB3     | 26 - 29 seconds |
| • BSB4     | 14 - 17 seconds |
| • FORD4    | 12 - 15 seconds |
| • ISO3     | 41 - 59 seconds |
| • ISO4     | 15 - 22 seconds |
| • ZAHN2    | 15 - 19 seconds |

*Note: Viscosities quoted are typical ranges obtained when using specified mix ratio.*



### **Pot Life:**

8 hours @ 21 - 25°C (70 - 77°F)

## Application Guidelines

### **Recommended Application Conditions:**

Temperature 15 - 35°C (59 - 95°F)  
Relative Humidity 35 - 70%

# PAC33 Polyurethane Primer

## Application:

Apply a double track coat or one wet coat with 50% overlap to achieve recommended dry film thickness of 15-25  $\mu\text{m}$ . Avoid applying higher film thicknesses as this can create orange peel and possible intercoat adhesion failures.




## Theoretical Coverage: (ready for use)

8 - 9  $\text{m}^2$  Lt @ 20  $\mu\text{m}$  dry film thickness  
320 - 360  $\text{ft}^2$  US gal @ 0.8 mil dry film thickness

## Recommended Dry Film Thickness:

15 - 25  $\mu\text{m}$   
0.6 - 1 mil



## Dry Film Density:

1.7  $\text{g}/\text{cm}^3$   
14 lbs/US gal

## Dry Film Weight:

34  $\text{g}/\text{m}^2$  @ 20  $\mu\text{m}$  dry film thickness  
0.006 lbs/ $\text{ft}^2$  @ 0.8 mil dry film thickness

*Note: These application guidelines represent PPG's best advice for usage in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.*

**Equipment:** PAC33 is compatible with all current types of spray equipment.



Equipment	Tip Size	Flow Rate	Air Pressure
Airmix Kremlin	$\varnothing = 0.28\text{mm}$ – Angle 60° Ref: 06.134	320 to 360 ml/min	725 to 870 psi (50 to 60 bar)
HVLP	1.2 mm		22 to 29 psi (1.5 to 2 bar)
Conventional Air Spray	1.5 mm		43 to 58 psi (3 to 4 bar)
Airless	Not Recommended		
Airless Air-assisted	609 to 611	360 ml/min	725 to 870 psi (50 to 60 bar)
PRO 3500 or Pro XS4	1.2 to 1.5 mm	360 ml/min	72 to 87 psi (5 to 6 bar)

## Equipment Cleaning:

Clean spray equipment before use and as soon as possible after use. DeSoto® CN20, CN44 or Desoclean™ 45 solvent cleaners are recommended.

# PAC33 Polyurethane Primer

## Physical Properties



**Colour:**  
Green




**Gloss:**  
Not Applicable

Drying Times @ 50 % R.H.	23°C (73°F)	60°C (140°F)	80°C (176°F)	100°C (212°F)
Dust Free	30 minutes			
Dry to Handle	1 hour			
Dry to Mask	2 hours			20 minutes
Dry to Sand	2 hours			
Dry to Overcoat with topcoat CA8000, CA8800 or 9008 BC	1 hour (min.) 72 hours (max.)			
Dry to Overcoat with 7049 or CA7002 Primer	4 hours (min.) 72 hours (max.)			
Dry to Overcoat	1 hour (min.) 72 hours (max.)			
Dry to Fly	48 hours (min.)			
Full Cure	7 days	2 hours	1.5 hours	



*Note: Drying times listed above are dependent upon film thickness applied, air flow conditions and application technique.*



**Flash Off Time:**  
20 minutes at 23°C (73°F) prior to accelerated cure.



**VOC: (ASTM)**

Mixed ready for use	730 g/Lt
4355/ Base Component	700 g/Lt
0701/9000 Activator	270 g/Lt
0433/9000 Thinner	880 g/Lt



**Flash Point:**

4355/3600 Base Component	2°C (36°F)
0701/9000 Activator	42°C (108°F)
0433/9000 Thinner	4°C (39°F)


# PAC33 Polyurethane Primer

## Shelf Life:

4355/3600 Base Component	24 months in original unopened container
0701/9000 Activator	24 months in original unopened container
0433/9000 Thinner	10 years in original unopened container

*Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.*

## Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

*Note: When procuring to a qualified material specification, follow those storage instructions.*

# PAC33 Polyurethane Primer

## Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

**For industrial use only. Keep away from children.**

**Additional information can be found at: [www.ppgaerospace.com](http://www.ppgaerospace.com)**

**For sales and ordering information call the local PPG office at the numbers listed below:**

### **Asia Pacific**

#### **ASC – Australia**

Tel 61 (3) 9335 1557

Fax 61 (3) 9335 3490

#### **ASC – Japan**

Tel 81 561 35 5200

Fax 81 561 35 5201

#### **ASC – South East Asia**

Tel 65 6861 1119

Fax 65 6861 6162

#### **ASC – Suzhou**

Tel (86-512) 6661 5858

Fax (86-512) 6661 6868

#### **ASC – Tianjin**

Tel (86-022) 2482 8625

Fax (86-022) 2482 8600

### **Europe and Middle East**

#### **ASC – Central Europe**

Tel 49 (40) 742 193 10

Fax 49 (40) 742 139 69

#### **ASC – Middle East & India**

Tel (971) 4 883 9666

Fax (971) 4 883 9665

#### **ASC – North Europe**

Tel 44 (0) 1388 770222

Fax 44 (0) 1388 770288

#### **ASC - South Europe**

Tel 33 (0) 235 53 43 71

Fax 33 (0) 235 53 54 44

### **Americas**

1 (818) 362-6711 or 1-800-AEROMIX

**Desoclean, Desothane, and DeSoto are trademarks of PRC-DeSoto International, Inc.**

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

*This document has been reviewed by the PPG Aerospace Export Control Department and has been determined to contain only EAR99 controlled data.*

PPG Aerospace  
Sealants and Coatings  
Darlington Road  
Shildon, Co Durham UK  
DL4 2QP  
[www.ppgaerospace.com](http://www.ppgaerospace.com)  
Issue Date: 02/24  
Lit: 4215