

Desoprime™ 7531 Chromate Free Etch Primer

Product Description

7531 is a Chromate Free Etch Primer suitable for use in both land based and aerospace applications. It has been specifically developed for use with the UK Military system Desoprime™ 7521 Chromate Free Primer and Desothane™ 83XX HS PU Topcoats.

- Excellent corrosion resistance
- Excellent adhesion to aluminium and steel substrates
- Phenolic modified for excellent water resistance
- Used to reactivate aged anodized or chromated surfaces
- Easy to apply in a wide range of environmental conditions
- Lower VOC than conventional Etch and Wash Primers



Components

Mix Ratio (by volume)

- 7531 (Base) 1 part
- 7531B (Activator) 1 part

Specifications



7531 is qualified to:

- PPG Standard

Product Compatibility

7531 is compatible with the following primer specifications:

- DEF STAN 80-225
- DGQT 1.7.0.0150
- HMRC0154
- BS2X33

Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.

Surface Preparation and Pretreatment



Ensure the surface is clean, dry and intact using a high performance solvent cleaner - DeSoto® CN20 or Desoclean™ 45 solvent cleaner are recommended.

Instructions for Use



Thoroughly shake the CF Etch Primer Base component (7531) for a minimum of 3 minutes until a smooth and homogenous mix is obtained. Slowly add 1 volume of CF Etch Primer Activator (7531B) to 1 volume of base (7531) whilst stirring.

Note: All products and components should be placed in ambient conditions of 15-35°C (59-95°F) for at least 24 hours prior to mixing and application.



Induction Time:

Not required



Viscosity: (23°C/73°F)

- ISO 4 27 - 42 seconds
- #2 Signature ZAHN cup 25 - 30 seconds

Note: Viscosities quoted are typical ranges obtained when using specified mix ratio.



Pot Life:

4 hours @ 15-35°C (59-95°F)

Application Guidelines

Recommended Application Conditions:

Temperature 15 - 35°C (59 - 95°F) Relative

Humidity 30 - 85%

Application:


Apply a light, wet, closed film to achieve a dry film thickness of 4 - 10 µm.



Note: Over application / excessive film build of product will result in a dark blue discolouration of the dry film.



Theoretical Coverage: (ready for use with mix ratio 1:1)
26 m²/Lt @ 7 µm dry film thickness



Dry Film Density:
1.04 g/cm³

Equipment:



Equipment Type	Tip Size	Pressure
Conventional Spray Gun	1.2 mm to 1.4 mm	1.5-3 bar
HVLP	1.2 mm to 1.4 mm	1.5-3 bar

Note: Contact your local Technical Service Representative for information on use of alternative application equipment.

Equipment Cleaning:

Clean spray equipment before use and as soon as possible after use. DeSoto® CN20, CN44, Desoclean™ 45 or PPG MB28 solvent cleaners are recommended.

Note: These application guidelines represent PPG's best advice for usage in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables

Physical Properties



Colour:
Blue



Gloss:
Not Applicable



Drying Times

Drying Times at 23°C (73°F) 55% R.H.	
Dry to Touch	20 minutes
Dry To Handle	30 minutes
Dry To Overcoat	1 to 72 hours
Dry to Mask	1.5 hours
Full Cure	7 days

Note: Drying times listed above are dependent upon film thickness applied, air flow conditions and application technique

Note: 7531 should not be force dried at temperatures above 60°C (140°F) unless already overcoated with another product.

VOC

VOC: (ASTM)

Mixed ready for use	650 g/Lt
7531	500 g/Lt
7531B	800 g/Lt

Flash Point:

7531	-4°C (25°F)
7531B	-4°C (25°F)



Shelf Life:

7531	24 months in original unopened container
7531B	24 months in original unopened container

Note: Shelf life may vary due to OEM specification requirements. Refer to container label for specific shelf life information.

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life. **Note:** *When procuring to a qualified material specification, follow those storage instructions.*

Health Precautions

This product is safe to use and apply when recommended precautions are followed.

Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

Additional information can be found at: www.ppgaerospace.com

For sales and ordering information call the local PPG office at the numbers listed below:

Asia Pacific

ASC – Australia

Tel 61 (3) 9335 1557

Fax 61 (3) 9335 3490

ASC – Japan

Tel 81 561 35 5200

Fax 81 561 35 5201

ASC – South East Asia

Tel 65 6861 1119

Fax 65 6861 6162

ASC – Suzhou

Tel (86-512) 6661 5858

Fax (86-512) 6661 6868

ASC – Tianjin

Tel (86-022) 2482 8625

Fax (86-022) 2482 8600

Europe and Middle East

ASC – Central Europe

Tel 49 (40) 742 193 10

Fax 49 (40) 742 139 69

ASC – Middle East & India

Tel (971) 4 883 9666

Fax (971) 4 883 9665

ASC – North Europe

Tel 44 (0) 1388 770222

Fax 44 (0) 1388 770288

ASC - South Europe

Tel 33 (0) 235 53 43 71

Fax 33 (0) 235 53 54 44

Americas

1 (818) 362-6711 or 1-800-AEROMIX

Desoclean and DeSoto are trademarks of PRC-DeSoto International, Inc.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

This document has been reviewed by the PPG Aerospace Export Control Department and has been determined to contain only EAR99 controlled data

PPG Aerospace
Sealants and Coatings
Darlington Road
Shildon, Co Durham UK
DL4 2QP

www.ppgaerospace.com

Issue Date: 01/2022

Lit: TBC